

Finkote Chemical Resistant Chart



Acetone	Fructose	Ozone
Acetic Acid	Gasoline	Perchloric Acid
Acetates (ALL)	Glucose	Phenol 85%
Amines (ALL)	Glycol	Phosgene
Ammonia	Glycol Ether	Phenolphthalein
Ammonium Hydroxide	H <sub>2</sub> CO <sub>3</sub>	Phosphoric Acid
Amino Acids	Hydrochloric Acid	Potassium Chloride
Benzene	Hydrofluoric Acid	Potassium Hydroxide
Borax	Hydrogen Peroxide 5%	Propyl Alcohol
Boric Acid	Hydrogen Sulfide	Propylene Glycol
Butyl Alcohol	Hydrazine	Salicylic Acid
Butyl Cellosolve	Hydroxylamine	Salt Water
Butyric Acid	Iodine	Sodium Bisulfite
Calcium Chloride	Isobutyl Alcohol	Sodium Chloride
Calcium Hypochlorite	Isopropyl Alcohol	Sodium Hypochlorite 5%
Carbon Tetrachloride	Kerosene	Sodium Hydroxide <10%
Cetyl Alcohol	Lactic Acid	Sodium Sulfate
Chlorides (ALL)	Lauryl Acid	Stearic Acid
Chlorine Gas	Magnesium	Sucrose

Finkote Chemical Resistant Chart

Chromic Acid (NR)	Maleic Acid	Sulfuric Acid 25-28%
Citric Acid	Menthol	Sulfates (ALL)
Creosol	Methanol	Sulfides (ALL)
Diesel Fuel	Methylene Chloride	Sulfites (ALL)
Diethanolamine	Methyl Ethyl Ketone	Starch
Ethyl Acetate	Methyl Isobutyl Ketone	Toluene
Ethyl Alcohol	Mustard Gas	Triethanolamine
Ethyl Ether	Naphthol	Xylene

\*100 Hour exposure time at ambient temperature. No Effect.