

FinkOTE2

Test	Specification	Results
SWAAT Run to Fail	ASTM G85 A3	289 days (6936 hrs)
30 Day SWAAT + Adhesion	ASTM G85 A3, ASTM D3359	Pass, 4B
2400 hr. Cyclic Corrosion + Burst	ASTM G85 A2	Pass, 2100 psi.
Water Resistance	ASTM D870-09	Pass, 260 hrs. no flaking or chipping
Chipping Resistance	ASTM D3170	Pass, 7A
Steam Resistance	ASTM D714	Pass, 48hr. #6 or better
Humidity Resistance	ASMT D2247	Pass, 600 hrs. no blistering or gloss loss
UV & QUV Resistance	ASTM G53-88, D4587, D523	1000 hrs. no loss
Chemical Resistance		48 hrs. immersion resistance to over 200+ chemicals
Heat Transfer		<3%
Thickness	ASTM 376	.8-1.2 mil (E-coat) 1.8-4 mil (total)
Flexibility	ASTM D4145, ASTM 522	2T, 5/8" mandrel
Impact Resistance	ASTM D2794-93	120 in. lbs. no cracking or chipping
Adhesion	ASTM 3359	5B

FOR MORE INFORMATION CONTACT:

CENTRAL LOCATION
Oklahoma Custom Coating
Seminole, OK
(405) 382-0231
sales@finkote.us

SOUTH LOCATION:
Metal Processing International
Mission, TX
(956) 205-0083
sales@finkote.us

www.finkote.us